

HIGHLY ORIENTED UNDRAWN YARN OF POLYPROPYLENE TEREPHTHALATE AND ITS PRODUCTION

Patent Number: JP2001064824
Publication date: 2001-03-13
Inventor(s): KANNO KOJI;; MOCHIZUKI KATSUHIKO;; MAEDA YUHEI
Applicant(s): TORAY IND INC
Requested Patent: ☐ JP2001064824
Application Number: JP19990238239 19990825
Priority Number(s):
IPC Classification: D01F6/62; D02J1/08; D02J1/22
EC Classification:
Equivalents:

Abstract

PROBLEM TO BE SOLVED: To produce a highly oriented undrawn yarn of polypropylene terephthalate capable of suppressing problems in a conventional two-step method for the highly oriented undrawn yarn of the polypropylene terephthalate, i.e., a change in filaments with time after spinning, imparting flexibility to the production and improving productivity and to provide a method for producing the yarn.

SOLUTION: This highly oriented undrawn yarn of polypropylene terephthalate comprises polyester filaments in which at least 90 mol% of polymer components forming the filaments are composed of propylene terephthalate units and satisfies the following formulae (1) to (4): (1) strength ST (g/d): $2.0 \leq ST$, (2) birefringence Δn (10-3): $30 \leq \Delta n \leq 60$, (3) elongation EL (%): $80 \leq EL \leq 250$ and (4) shrinkage percentage in boiling water SW (%): $3 \leq SW \leq 15$.

Data supplied from the esp@cenet database - I2